PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ³ :		(11) International Publication Number: WO 81/02256		
B01D 53/04	A1	(43) International Publication Date: 20 August 1981 (20.08.81)		
(21) International Application Number: PCT/US (22) International Filing Date: 3 February 1981 (ropean patent), GB (European patent), JP.		
(31) Priority Application Number:	118,5	Published With international search report		
(32) Priority Date: 4 February 1980 (04.02.8	0)		
(33) Priority Country:	τ	JS		
 (71) Applicants; and (72) Inventors: UNDERHILL, Dwight, W. [US/U Centre Avenue, Pittsburgh, PA 15206 (US). James, R. [US/US]; 23 MacArthur Road, V MA 02181 (US). (74) Agents: BROOK, David, E. et al.; Hamilton Smith & Reynolds, 2 Militia Drive, Lexing 02173 (US). 	LASKI Wellesle	E, ey, bk,		

(54) Title: IMPREGNATED CHARCOAL FOR REMOVING RADIOACTIVE MOLECULES FROM GASES

(57) Abstract

Impregnated adsorbent for removing radioactive molecules from gas wherein charcoal is impregnated by spraying or other simple techniques with a substituted 1,4-diazabicy clo[2.2.2]octane which is a liquid at atmospheric pressure and a range of normal operating temperatures.

FOR THE PURPOSES OF INFORMATION ONLY

He was made . . Copy of the the fight

tin de la companya d La companya de la co La companya de la co

ទូលី ទី២៨៩៦១៤ មួយសម្រាស់ ១០១ ១៤ ខ័ណ្ឌ មក ប្រទៅខ្នះ ១៣

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

		770	Democratic People's Repu	hio of Kores
AT	- Austria	KP LI	Liechtenstein	ione of Rolea
ΑŪ	Australia		Luxembourg	
	Brazil Central African Republic	LU		
CF	Central African Republic		Monaco	1 .
CG	Congo	MG	Madagascar	
CH	Switzerland	MW	Malaŵi	
CM .	Cameroon	NL	Netherlands	
DE	Germany, Federal Republic of	NO NO	Norway	• "
DK	Denmark	RO	Romania	
FI .	Finland France	SE,	Sweden	
FR	France		Senegal.	
GA	Gabon	SU	Soviet Union	
GB	United Kingdom	TD	Chad	
HU	Hungary	TG	Togo	
JР	Japan	US	United States of America	

IMPREGNATED CHARCOAL FOR REMOVING RADIOACTIVE MOLECULES FROM GASES

Description

Technical Field

This invention is in the field of adsorbent materials for removing radioactive molecules, such as methyl iodide, from gases.

Background Art

It is often necessary to trap or remove radio10 active molecules from gases. This is particularly true
regarding nuclear energy plants, where off-gas streams
often contain radioactive molecules, including alkyl
halides such as methyl iodide. Such radioactivity
is usually caused by isotopes, such as iodine 131.


A common method employed for removing radioactive molecules from such gas streams involves the use of gas filtration systems containing beds of adsorbent materials, such as charcoal. When used in this capacity, charcoal is frequently treated to 20 increase its surface area; such treated charcoal is frequently called activated charcoal, and is intended to be included within the term charcoal as used herein. Such adsorbent beds are normally operated at room temperatures although they must be capable of with-25 standing higher temperatures under emergency conditions.

To increase the adsorption efficiency of such beds, the adsorbent may be impregnated with substances



that increase its tendency to adsorb certain molecules such as alkyl halides. Examples of impregnants previously used with activated charcoal for this purpose are set forth in U.S. Patent No. 3,453,807, issued to R. Taylor in 1969.

In the Taylor patent, activated charcoal is impregnated with a water-soluble secondary or tertiary amine. One such tertiary amine (referred to in the claims as a secondary amine) is stated to be triethylenediamine (TEDA), which might also be named 1,4-diazabicyclo[2.2.2]octane. This substance can be represented by the following chemical formula:



While 1,4-diazabicyclo[2.2.2]octane has proven to be somewhat suitable for trapping radioactive alkyl 15 halides and other molecules, it suffers from several disadvantages. One significant disadvantage is that this substance is a crystalline solid at atmospheric pressure and normal operating temperatures. Therefore, it must be dissolved in a solvent, such as water, prior 20 to application to the charcoal. This has proven to be a complex and troublesome operation in the production of impregnated charcoal. In addition, this substance tends to be relatively volatile. Therefore, it tends to escape from impregnated charcoal through the process 25 of sublimation. Find here have the many in

1,4-diazabicyclo[2.2.2]octane can be modified to render it a liquid at atmospheric pressure over a substantial range of temperatures. This can be accomplished by substituting any of several groups for one of the hydrogen atoms on the 1,4-diazabicyclo[2.2.2]-



octane. Such appended groups disrupt the symmetrical shape of the unsubstitued molecules, reducing its tendency to crystallize. Such substituted compounds can be represented by the following structural formula:

wherein the combination of R substituents, one or more of which are not hydrogen, cause the compound to be a liquid at atmospheric pressure.

Suitable R substituents can comprise lower alkyl groups, i.e., C₁-C₆ alkyl. Examples of such compounds include 2-methyl-1,4-diazabicyclo[2.2.2] octane; 2,5-dimethyl-1,4-diazabicyclo[2,2,2] octane; 2,6-dimethyl-1,4-diazabicyclo[2.2.2]octane, 2-ethyl-1,4-

15 diazabicyclo[2.2.2]octane; 2,5,7-trimethyl-1,4-diazabicyclo[2.2.2]octane; and 2-propyl-1,4-diazabicyclo [2.2.2]octane. These alkyl-substituted compounds are described in the patent literature in U.S. Patent Nos. 3,297,701 (Brader et al, 1967) and 3,325,547 (Cour.

20 et al, 1967); British Patent No. 1,045,091 (Farkas et al, 1966); and German Offen. No. 2,215,474, the teachings of which, in regard to the syntheses and properties of these compounds, are hereby incorporated by reference. Alternately, charcoal may be impregnated with an

25 aqueous mixture containing a tertiary amine (such as diazabicyclo[2.2.2]octane) and an inorganic salt of iodine or bromine, as described in U.S. Patent No. 4,040,802 (Dietz et al., 1977).

German Offen. 2,629,302 (Dabby, 1977) reveals the 30 use of impregnant compounds substituted with lower alkyl groups, such as 2-methyl-1,4-diazabicyclo[2,2.2]octane,



applied to the adsorbent material alumina. However, the process of applying the impregnant to the alumina is complex and wasteful. In addition, that document does not disclose information about the kinetics of the adsorption reaction, e.g., the rate at which gas is diffused through the material and the rate at which the alkyl halides are adsorbed on the impregnated alumina. Rapid adsorption rates are very important in the use of adsorbents to remove radioactive molecules from nuclear reactor off-gases.

Disclosure of the Invention

The invention described herein arises out of the discovery that several surprising and very useful results occur when 1,4-diazabicyclo[2.2.2]octane, which has been substituted to make it a liquid at room temperature and atmospheric pressure, is applied to charcoal that is used as an adsorbent for radioactive gases. These advances are substantially superior to the prior art regarding both unsubstituted 1,4-diazabicyclo[2.2.2]octane, used as an impregnate on charcoal, as well as substituted 1,4-diazabicyclo-[2.2.2]octane used as an impregnate on alumina.

The first surprising advantage relates to the 25 process of applying the impregnate to the adsorbent. When applying substituted 1,4-diazabicyclo[2.2.2]-octane, German Offen. 2,629,302 required the adsorbent to be pre-heated under a vacuum, cooled, treated with excess impregnate, and allowed to 30 stand for an hour. The excess impregnate was then removed, by an undisclosed process. The sorbent was then dried for several hours in a vacuum oven; presumably, impregnate that evaporated during that period was either recycled or disposed of.



Unexpectedly, it has been discovered that the process of applying substituted 1,4-diazabicyclo-[2.2.2]octane to charcoal is a great deal simpler than the process of applying this same material to 5 alumina. This apparently results from very substantial differences between the pore structure within and diffusion rates through the two adsorbents. The inventors have discovered that the application of substituted 1,4-diazabicyclo[2.2.2]octane does not re-10 quire pretreatment of the adsorbent with heat and vacuum, nor the use of excess impregnate, nor the removal of excess impregnate. Instead, substituted 1,4-diazabicyclo[2.2.2]octane can be applied to charcoal through a single operation, such as conventional 15 spraying. If the impregnate is simply sprayed over charcoal absorbent, it will tend to diffuse by capillary action, forming a relatively uniform thin film on very large areas of the charcoal. This is in marked and unexpected contrast to the diffusion of the same 20 compound when applied to alumina.

Several other fluid application techniques can also be used to apply substituted 1,4-diazabicyclo-[2.2.2]octane to charcoal. For example, the impregnate could be vaporized and allowed to condense upon 25 the adsorbent. Alternately, the charcoal could be immersed fully or partially in the impregnate, which would coat the charcoal by capillary action.

The second major advantage of using charcoal rather than alumina results from the fact that charcoal 30 has a much greater surface area than the same quantity of alumina. A gram of high-quality charcoal has a total surface area of approximately 1,000 to 1,500 square meters, while a gram of adsorbent alumina has a surface area of approximately 100 to 350 square meters.

35 Therefore, charcoal will tend to retain more impregnate and more radioactive molecules than will alumina.



Another benefit which can be obtained by employing charcoal instead of alumina derives from the fact that charcoal is relatively more hydrophobic than alumina. Therefore, both impregnate molecules and alkyl halides will tend to adsorb more readily to charcoal than to alumina in the presence of substantial humidity, a condition which normally exists in the nuclear reactor uses contemplated by this invention. Impregnate molecules and alkyl halides will also tend to bond more tightly to charcoal than to alumina, thereby being retained more efficiently in the adsorbent bed.

A still further surprising result obtained by using charcoal rather than alumina as adsorbent material is the rate at which radioactive molecules

15 cling to impregnated charcoal. As described in the examples below, a gas stream containing radioactive methyl iodide was passed through an impregnated charcoal bed with a contact time of only about one-fourth of a second. However, the impregnated charcoal removed substantially more than 99% of the input methyl iodide.

Best Mode of Carrying Out the Invention

This invention employs charcoal as an adsorbent material to remove radioactive molecules from gas.

The appropriate particle size, bed configuration

25 and dimensions, pretreatment techniques, and other such parameters relating to the use of charcoal in this capacity can be chosen for each application. In general, such parameters will be known to those skilled in the art, or can be determined using no more than routine experimentation.

The charcoal is impregnated with a substituted 1,4-diazabicyclo[2,2,2]octane, wherein the substituent(s) causes the substituted compound to be a liquid at atmospheric pressure and room temperatures.



5

One preferred impregnant is 2-methyl-1,4-diazabicyclo[2.2.2]octane, which also can be called methyl-triethylene diamine. This substance can be represented by the following formula:

The impregnate is applied to charcoal by any of several conventional fluid handling techniques. A preferred way to apply impregnate to charcoal is by spraying the impregnate with a nebulizer using air pressure. Impregnation can be accomplished before the charcoal is loaded into an adsorbent bed, or after unimpregnated charcoal is loaded into an adsorbent bed with suitable dimensions and configuration.

Other agents can be added to the specific liquid

15 impregnant chosen, prior to its application to the charcoal. Similarly, two or more diffirent liquid impregnants according to this invention could be mixed together. It is also possible to dissolve unsubstituted crystalline 1,4-diazabicyclo[2.2.2]octane in

20 one or more of the liquid impregnants described herein, such as 2-methyl-1,4-diazabicyclo[2.2.2]octane. All such possibilities are included within the scope of this invention.

The amount of impregnate employed for any given 25 application can vary. In general, amounts between about one percent and about ten percent by weight, based upon the weight of unimpregnated adsorbent, are considered suitable.

Once the impregnated charcoal is loaded into

30 an adsorbent bed, the bed is installed within a gas
handling system using conventional technology. A



preferred way to install an adsorbent bed in a nuclear reactor is to install the bed by means of piping and valves between a source of radioactive gas and an outlet to the atmosphere. Any gas that is released by the reactor to the atmosphere must pass through the adsorbent bed, which removes radioactive molecules from the gas before it is released.

Example 1

Charcoal derived from a coconut base material,

8/16 mesh, steam activated, and having a surface
area of about 1,000 square meters per gram was
employed. Before the test began, the charcoal
was pre-equilibrated with air at 25°C, 95% relative
humidity, in order to obtain reproducible results.

15 About 4.5%, by weight, 2-methyl-1,4-diazabicyclo[2.2.2] octane was then sprayed upon the charcoal
with a nebulizer at about 60 pounds of air pressure.
The additional test conditions were:

Temperature - 25°C

20 Bed Depth - 2 inches

Air Velocity - 7.84 inches/second

Contact time - 0.254 seconds

Relative humidity - 95%

Pressure - Atmospheric

Concentration of radioactively labelled
Methyl Todide - 2 mg/meter³

Feed Duration - 2 hours Elution Period - 2 hours.

At the end of the four hour test period, 99.92% of
the methyl iodide had been retained within the test bed.
As much as 3.0% of the methyl iodide could have passed through the charcoal and still met a currently existing commercial standard.



PCT/US81/00144

Example 2

10

15

25

Charcoal impregnated with 2-methyl-1,4-diazabicylo-[2.2.2]octane, prepared as described in Example 1, was tested at a relatively high temperature. The test

5 conditions were:

Temperature - 130°C

Relative Humidity - 95%

Bed Depth - 2 inches

Air Velocity - 8 inches/second

Contact time - 0.25 seconds

Pressure - 42.5 psia

Concentration of radioactively

labelled Methyl Todide - 1.75 mg/m³

Feed Duration - 2 hours

Elution Period - 2 hours

Under these conditions, the impregnated charcoal retained 99.75% of the input methyl iodide.

Industrial Applicability

The invention described herein has industrial applicability in nuclear power plants and other such applications wherein it is desirable and/or necessary to remove radioactive molecules, such as methyl iodide, from a volume of gas.

Equivalents

Those skilled in the art will recognize, or be able to ascertain using no more than routine experimentation, many equivalents to the embodiments specifically described herein. Such equivalents are intended to be covered by the following claims.

Court to to to be

5 . St. 1 * 8 2 4 65 . W.

r care frid. I a I so recentified




Claims

1. In the use of charcoal for removing radioactive molecules from gas:

The improvement wherein said charcoal is impregnated with a substituted 1,4-diazabicyclo[2.2.2]octane which is a liquid at room temperature and atmospheric pressure.


2. An adsorbent comprising charcoal impregnated with a compound represented by the structural formula:



wherein R₁ through R₁₂ are substituents which cause the compound to be a liquid at room temperature.

- 3. An improvement of Claim 2 wherein at least one of the R substituents comprises a lower alkyl group.
- 4. An improvement of Claims 2 or 3 wherein one of the R substituents comprises a methyl group and the other R substituents are hydrogen.
- 5. A charcoal adsorbent impregnated with 2-methyl, 1,4-diazabicyclo[2.2.2]octane.
- 6. A method for trapping radioactive gaseous products in a gas stream by passing said gas stream through charcoal impregnated with a substituted 1,4-diazabicyclo[2.2.2]octane which is a liquid at room termperature and atmospheric pressure.

7. A method of Claim 6 wherein said substituted 1,4-diazabicyclo[2.2.2]octane is a compound represented by the structural formula:



wherein R₁ through R₁₂ are individually selected from hydrogen and lower alkyl groups.

- 8. A method of applying an impregnate comprising 1,4-diazabicylo[2.2.2]octane to an adsorbent comprising the following steps:
 - a. substituting for one or more of the hydrogen atoms on said 1,4-diaza-bicyclo[2.2.2]octane a substituent group selected so that the resulting compound is a liquid at room temperature and atmospheric pressure; and
 - b. applying said substituted impregnate to said adsorbent by a technique selected from the following group of techniques: spraying, condensation, partial immersion, and total immersion

the way of mercining the

while a list to be thought he share will

9. An improvement of Claim 8 wherein at least one said substituent group comprises a lower alkyl group.

office of the second of the second

FURTHE	RINF RMATION C NTINUED FR M THE SECOND SHEET	a t
A	US, A, 3,491,031 Published 20 January 1970,	1-9
	Stoneburner.	
A	US, A, 4,016,242 Published 05 April 1977,	1-9
* .	Deitz et al.	
Α	US, A, 4,11,833 Published O5 September 1978,	1-7
	Evans.	
A,P	US, A, 4,204,980 Published 27 May 1980,	1-9
	. Pasha et al.	
•		
V OB	SERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE 10	
	national search report has not been established in respect of certain claims under Article 17(2) (a) for	the following reasons:
	m numbers because they relate to subject matter 12 not required to be searched by this Auth	
		* *
		,
	m numbers, because they relate to parts of the international application that do not comply witte to such an extent that no meaningful international search can be carried out 18, specifically:	ih the prescribed require-
VI. O	SERVATIONS WHERE UNITY OF INVENTION IS LACKING 11	
This Inte	mational Searching Authority found multiple inventions in this international application as follows:	
	The color of the second of	
	all required additional search fees were timely paid by the applicant, this international search report co ne international application.	vers all searchable claims
	only some of the required additional search fees were timely paid by the applicant, this international assets of the International application for which fees were paid, specifically claims:	earch report covers only
• • •		ta de la companya de
		8
the	required additional search fees were timely paid by the applicant. Consequently, this international sear Invention first mentioned in the claims; it is covered by claim numbers:	ch report is restricted to
	الا بالداعلية والمدينة الداعلية والالمداع والمجارة والمجارة والمحافظة والمداعلة المداعدة المداعدة المداعدة الم والمداعدة المدينة الداعدة المدينة المحدودة المدينة والمداعدة المدينة المدينة المدينة والمحدود المدينة المدينة	
	the control of the transfer that the transfer which is a first the first of the fir	
	n Protest additional search fees were accompanied by applicant's protest.	
=	protest accompanied the payment of additional search fees.	

Form PCT/ISA/210 (supplemental sheet (2)) (October 1977)

I. CLAS	SIFICATI	N OF SUBJECT MATTER (if several class		C1/0881/00144
Accordi	ng to Interna	tional Patent Classification (IPC) or to both Na	tional Classification and IPC	
INT.	CL.3	B01D 53/04		
U.S.	CL.	55/71		
II. FIELI	DS SEARC	HED		
			intation Searched 4	
Classifica	tion System		Classification Symbols	
		55/35,71,74,387; 252/428;	; 521/174; 526/210;	•
v.s.		544/351		
		1		
		Documentation Searched other to the Extent that such Documents	than Minimum Documentation B are included in the Fields Searched 5	
,			3	
				•.
NONE				
III. DOC	UMENTS (CONSIDERED TO BE RELEVANT 14		
Category *	Cita	ion of Document, 16 with indication, where app	propriate, of the relevant passages 17	Relevant to Claim No. 18
x	US. A.	4,040,802 Published 0	19 August 1977.	1-7
	,,		, nagase 1, , ,	1 .
		Deitz et al.	<u></u> = 5 4 -	
X		3,297,701 Published 1	10 January 1967,	3-4,7
]_,	Brader, Jr. et al.		
x	US, A,	2,818,323 Published 3	31 December 1957,	8-9
		Haensel.	7"	
A	TIC A.	3,015,368 Published 0	19 Tanuary 1969	1-5, 8-9
4.	100,,		/L vanuas, 1500,	1 2, 2
		Reid.		
A	US, A,	3,112,320 Published 2	26 November 1963,	, 1–5
		Farkas.	;	
A	US, A,	3,325,547 Published 1	3 June 1967,	1-5
-	6		FILE of the second	•
A -	}	3,429,103 Published 2	######################################	1-9
A	UD, A,		D redruary 1909,	1-2
		Taylor.	÷.	1
A	US, A,	3,453,807 Published 0	08 July 1969,	1-9
		Taylor.	<u> </u>	
		i safi i militar ya kazari ki militari		
2 5	<u> </u>			!
	-	of cited documents: 15	#P" document published prior to the l	
"E" earlie		but published on or after the international	on or after the priority date claime	d
"L" docu	ment cited	or special reason other than those referred	"T" later document published on or af date or priority date and not in co	offict with the application.
	the other o	ng to an oral disclosure, use, exhibition or	but cited to funderstand the prince the invention w	tiple or theory underlying
othe	r means	The state of the s	Tax document of particular relevance	<u> </u>
	PIFICATIO	mpletion of the International Search 2	Date of Mailing of this International Se	arch Donort 2
		mplead. d. ald meaning. Canton	2 1 1	•
12 Ma	y 1981		<u> </u>	1301
Internatio	nal Searchin	g Authority 1	Signature of Authorized Office	
TCA /II	. ·		Popular H. Se	

Same Carla

Assirida Company

1.23

record

The state of the s

No. 100 Autous A

The control of the co

dirimbiştirin bili

PATENT COOPERATION TREATY

PCT

INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules, 43 and 44)

Applicant's or agent's file reference		of Transmittal of International Search Report
56684W0003	ACTION (FORM PC 17/1SA/2	20) as well as, where applicable, item 5 below.
International application No.	International filing date (day/month/year)	(Earliest) Priority Date (day/month/year)
PCT/US 02/05820	26/02/2002	10/05/2001
Applicant		
		
3M INNOVATIVE PROPERTIES	COMPANY	
This International Search Report has been according to Article 18. A copy is being tra	n prepared by this International Searching Auth ansmitted to the International Bureau.	nority and is transmitted to the applicant
·••		
This International Search Report consists		
X It is also accompanied by	a copy of each prior art document cited in this	report.
Basis of the report		
	international search was carried out on the bases otherwise indicated under this item.	sis of the international application in the
the international search w Authority (Rule 23.1(b)).	as carried out on the basis of a translation of t	he international application furnished to this
 b. With regard to any nucleotide an was carried out on the basis of the 	d/or amino acid sequence disclosed in the in	nternational application, the international search
	onal application in written form.	:
filed together with the inte	mational application in computer readable form	n. ,
furnished subsequently to	this Authority in written form.	,
furnished subsequently to	this Authority in computer readble form.	
the statement that the sul international application a	osequently furnished written sequence listing d is filed has been furnished.	loes not go beyond the disclosure in the
		s identical to the written sequence listing has been
	*	
	nd unsearchable (See Box I).	
3. Unity of invention is lac	king (see Box II).	
4 Night record to the state		·
4. With regard to the title, X the text is approved as su	shmitted by the applicant	
	shed by this Authority to read as follows:	•
the tox has been establish	wied by the Addionty to read as removed.	
		•
		•
5. With regard to the abstract,		
X the text is approved as su	ibmitted by the applicant.	,
	shed, according to Rule 38.2(b), by this Author e date of mailing of this international search rej	
6. The figure of the drawings to be pub		·
as suggested by the appl	_	X None of the figures.
because the applicant fail		<u> </u>
	characteriz s the invention.	•
		·

THE SEARCH HOMADS LAND

Land Barrell

表现是是100mm,100mm,200mm,200mm。 Committee of the state of the s

AN BENEVER OF BENEFIT PARK AND AND THE STATE OF AN ARMY AND AND AN ARMY AND A

A company

 $1 - \operatorname{CO}((n \operatorname{L} + \operatorname{CO}(n \operatorname{L} \operatorname{L}))) + (n \operatorname{L} \operatorname{L}) + (n \operatorname{L}$

21.7 1200

Property Strates and Strates

A second of the control of the control

Service of the pro-

T sasis

5-2965

INTERNATIONAL SEARCH REPORT

International Application No PCT/US 02/05820

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 B01J20/20 .

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols) IPC 7 $\,$ B01J $\,$ B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPQ-Internal

C. DOCUM	ENTS CONSIDERED TO BE RELEVANT	• • • • • • • • • • • • • • • • • • • •
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 455 173 A (SECR DEFENCE BRIT) 6 November 1991 (1991-11-06) claims	1-3,7
A	US 4 531 953 A (GROOSE JAMES E ET AL) 30 July 1985 (1985-07-30) cited in the application the whole document	1-3
A	EP 0 143 027 A (FRANCE ETAT) 29 May 1985 (1985-05-29) page 3, last paragraph -page 4, paragraph 1 page 6, line 19 - line 26; claims	1,7
Α.	WO 81 02256 A (UNDERHILL D;LASKIE J) 20 August 1981 (1981-08-20) page 5, line 1 - line 27	1-3

Further documents are listed in the continuation of box C.	Y Patent family members are listed in annex.
Special categories of cited documents: A' document defining the general state of the art which is not considered to be of particular relevance E' earlier document but published on or after the international filing date L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) O' document referring to an oral disclosure, use, exhibition or other means P' document published prior to the international filing date but later than the priority date claimed	 "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family
23 October 2002	Date of mailing of the international search report 31/10/2002
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Plaka, T

DESCRIPTION OF THE PROPERTY OF THE

INTERNATIONAL SEARCH REPORT

International Application No PCT/US 02/05820

Category °	tion) DOCUMENTS CONSIDERED TO BE RELEVANT Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.	
A	US 5 792 720 A (LEE HOO-KUN ET AL) 11 August 1998 (1998-08-11) claim 1	1-3	
		• •	
	4		
		•	

TO A STANDAR SEASON AND THE ACTION OF

with the end of the state of the

TO BOTHS OF THATO William A

The same about all a

....

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No PCT/US 02/05820

Patent document cited in search report .		. Publication date		Patent family : member(s)	Publication date
EP 0455173	Α	06-11-1991	CA EP US	2015810 A1 0455173 A1 5145820 A	01-11-1991 06-11-1991 08-09-1992
US 4531953	Α	30-07-1985	NONE		
EP 0143027	À	29-05-1985	FR DE EP	2553676 A1 3461686 D1 0143027 A1	26-04-1985 29-01-1987 29-05-1985
WO 8102256	A	20-08-1981	CA EP WO	1165303 A1 0045318 A1 8102256 A1	10-04-1984 10-02-1982 20-08-1981
US 5792720	A	11-08-1998	KR JP JP	155342 B1 2820650 B2 8333109 A	16-11-1998 05-11-1998 17-12-1996

ng ang mang panggang manggang panggang panggang panggang panggang panggang panggang panggang panggang panggang Banggang panggang pangganggang panggang panggang panggang panggang panggang panggang panggang panggang panggan Banggang panggang pa